

**GRADATION ANALYSIS TEST REPORT**  
**for Product: 03395/ 0/4 MP WASHED SAND**  
**Supplier/ source: South East - Northfleet**

Material type: Drystone aggregate Test method: Wash grading to BS EN 932-1: 1997

**SAMPLE INFORMATION**

Sampled/ tested  
 Thu 28 April 2022/ 10-05-22  
 at 0000 hrs

**Sample number** GDAT\_12775\_01BD

Location - Chainage/layer -  
 Ticket/truck number - Weather conditions -  
 Sampling notes - Aggregate type -  
 Remarks 1 - Remarks 2 -


**SAMPLE ANALYSIS**

Sieve size	Percent passing	Specification limits	Complies ?
8mm	100	100 - 100	yes
6.3mm	100	95 - 100	yes
5mm	100	-	-
4mm	97	85 - 100	yes
2.8mm	95	-	-
2mm	93	-	-
1mm	87	60 - 100	yes
500µm	63	30 - 70	yes
250µm	17	0 - 40	yes
125µm	1	-	-
63µm	0.2	0.0 - 3.0	yes
Moisture content %	3.7	not specified	-
Uniformity coefficient	3	=>1	yes
Chloride content %	0.028	<=0.300	yes

Parameters are evaluated to the accuracy of spec. limits

**REMARKS**

Compliance status ok  
 Category A of A-C includes secondary parameters



Signed \_\_\_\_\_

Print date 24 May 2022